

DIBAC

Diisobutylaluminum chloride

DIBAC is a co-catalyst product soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons.

CAS number
1779-25-5

EINECS/ELINCS No.
217-216-8

TSCA status
listed on inventory

Molecular weight
176.7

Characteristics

Appearance	Clear, colorless liquid
Boiling point, 1 mm Hg	108 °C
Density, 30 °C	0.904 g/cm ³
Melting point	-39 °C
Solubility	Soluble in aromatic and saturated aliphatic and cycloaliphatic hydrocarbons
Stability to air	Ignites upon exposure
Stability to water	Reacts violently, may ignite upon contact
Viscosity, 30 °C	4.0 mPa.s

Composition

Aluminum	^b 15.1-15.5 wt%
Cl/Al (molar)	1.00-1.05
Hydrogen	^a ≤ 0.6 molar%
Isobutane	^a ≥ 97.5 molar%
Isobutylene	^a ≤ 1.0 molar%
Other alkanes	^a -- molar%

Thermochemical properties

Heat of vaporization ΔH_v , NBP / 1 bar	^c 142 J/g (34 cal/g)
Heat of hydrolysis, 25 °C	2653 J/g (634 cal/g)
Specific heat, 57 °C	1.615 J/g.°C (0.386 cal/g.°C)
Heat of formation ΔH_f° , 25 °C / 1 bar	-498 kJ/mole (-119 kcal/mole)
Heat of combustion ΔH_c° , 25 °C	-6029 kJ/mole (-1441 kcal/mole)

Notes:

^a Calculated from gas chromatographic analysis of hydrocarbons and hydrogen obtained by hydrolysis. ^b Determined by titration of aqueous hydrolyzate. ^c NBP = normal boiling point

Applications

DIBAC is used as a cocatalyst in the Ziegler-Natta polymerization of olefins.

Storage

DIBAC and its solutions are stable when stored under a dry, inert atmosphere and away from heat. DIBAC slowly decomposes at temperatures above ~ 165°C.

Packaging and transport

DIBAC and its solutions are available worldwide in cylinders and portable tanks. In North America only, DIBAC is also available in tank trailers and rail cars. Containers are fabricated from carbon steel and are equipped with dip tubes for top discharge and all connections are located in the vapor space. Both packaging and transport meet the international regulations.

Safety and handling

DIBAC ignites upon exposure to air and reacts violently with water. Hydrocarbon solutions of DIBAC may also ignite upon exposure to air. DIBAC and its solutions must be handled under a dry, inert atmosphere, e. g. nitrogen or argon. Water must be scrupulously removed from process equipment prior to putting it into metal alkyls service. Failure to do so may result in an explosion. Products of complete combustion of DIBAC and its solutions are aluminum oxide, carbon dioxide, hydrogen chloride and water. DIBAC causes severe burns to the skin and eyes. It is imperative that proper personal protective equipment be worn when handling DIBAC. Please refer to the Material Safety Data Sheet (MSDS) for further information on the safe storage, use and handling of DIBAC. This information should be thoroughly reviewed prior to acceptance of this product. The MSDS is available at nouryon.com/sds-search.

Additional information

DIBAC is a commercial product available as the neat pyrophoric liquid and as pyrophoric and non-pyrophoric solutions in a variety of hydrocarbon solvents. Consult your Nouryon representative for further information.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Contact Us

Polymer Catalysts Americas
polymer.amer@nouryon.com

Polymer Catalysts Europe, Middle East, India and Africa
polymer.emeia@nouryon.com

Polymer Catalysts Asia Pacific
polymer.apac@nouryon.com

The logo for Nouryon, featuring a stylized blue 'N' followed by the word 'ouryon' in a lowercase, sans-serif font.