

Levasil CB75 LS

Colloidal silica

Levasil CB75 LS is an alkaline, aqueous dispersion of colloidal silica that is approximately 15% solids by weight. The silica dispersion is sodium stabilized and the amorphous silica particles carry a negative surface charge. The silica particles are structured to enhance the activity of the dispersion. The physical appearance of the dispersion is a clear liquid, slightly more viscous than water. Levasil CB75 LS is produced primarily for world-wide distribution.

CAS number
7631-86-9

Characteristics

Silica	15 wt%
Density	1.1 g/cm ³
pH	10
Viscosity	13 cP

Applications

Levasil CB75 LS is a specialty product designed primarily for hydraulically sealing geological formations and consolidation of soil and silt strata.

Storage

Levasil CB75 LS should be transported and stored at a temperature of 5-35°C (40-95°F). If the silica dispersion is allowed to freeze, the silica will irreversibly precipitate. For bulk storage, the tank should be sealed and constructed of plastic, fiberglass reinforced plastic, or stainless steel. For packaged goods, any translucent packages should be stored out of direct sunlight or bright light. Under recommended conditions, Levasil CB75 LS has a shelf life of at least 12 months after production.

Packaging and transport

Levasil CB75 LS is available in bulk and packaged quantities. Bulk shipping and packaging sizes can vary by region.

Safety and handling

Before handling this material, review the corresponding Material Safety Data Sheet. Colloidal silica products are aqueous dispersions of amorphous silica. Colloidal silica is not classified as harmful, but as mildly irritating. Because the products can have a drying effect on the skin, protective gloves should always be used. In case of skin contact, wash the area of contact with plenty of water. The use of safety glasses is always recommended. In case of eye contact, rinse with large amounts of water and seek professional medical advice.

All information concerning this product and/or suggestions for handling and use contained herein are offered in good faith and are believed to be reliable. Nouryon, however, makes no warranty as to accuracy and/or sufficiency of such information and/or suggestions, as to the product's merchantability or fitness for any particular purpose, or that any suggested use will not infringe any patent. Nouryon does not accept any liability whatsoever arising out of the use of or reliance on this information, or out of the use or the performance of the product. Nothing contained herein shall be construed as granting or extending any license under any patent. Customer must determine for himself, by preliminary tests or otherwise, the suitability of this product for his purposes. The information contained herein supersedes all previously issued information on the subject matter covered. The customer may forward, distribute, and/or photocopy this document only if unaltered and complete, including all of its headers and footers, and should refrain from any unauthorized use. Don't copy this document to a website.

Levasil® is a registered trademark of Nouryon Chemicals B.V. or affiliates in one or more territories.

Contact Us

Nouryon, Colloidal Silica, Kromasil

SE-445 80 Bohus
Sweden
+46 31 58 70 00
kromasil@nouryon.com

South America

Jundiai
Brazil
+55 11 45894800
colloidal.silica@nouryon.com

USA, Canada and Mexico

Marietta
USA
+1 770 5780858
colloidal.silica@nouryon.com

China

Shanghai
P.R.China
+86 21 22205000
levasil.china@nouryon.com

North and South East Asia

Taichung
Taiwan
+886 4 23270520
colloidal.silica@nouryon.com

Europe, Africa and Australia

Cologne
Germany
+49 221 995850
colloidal.silica@nouryon.com

Nouryon